

502-R-761 PORTLAND CEMENT CONCRETE PAVEMENT, PCCP

(Adopted 07-20-23)

The Standard Specifications are revised as follows:

SECTION 502, BEGIN LINE 114, DELETE AS FOLLOWS:

^c Beams shall be standard cured in a water tank in accordance with AASHTO T 23 and 505.01(a). The water does not need to be saturated with calcium hydroxide. ~~Minimum flexural strength for opening to traffic shall be in accordance with 506.12.~~
